

## MAXTEL 600GF30

MAXTEL 600GF30 is a 30% glass filled polypropylene. This material is available in black. It can be color matched black and either UV or non-UV stable. It is typically used for automotive interior/exterior applications. Please contact us for additional information.

### Typical ISO Properties

#### Properties

##### PHYSICAL

	Test Method		S. I. Units
Specific Gravity	ISO 1183	1.12	NA
Melt Flow Rate @ 230 °C/2.16kg	ISO 1133	7	g/10min
Reinforcement Content	ISO 3451	30	%

##### MECHANICAL

Tensile Strength @ Yield	ISO 527	56	MPa
Flexural Strength	ISO 178	87	MPa
Flexural Modulus	ISO 178	4,800	MPa
Izod Impact, notched	ISO 180	12	kJ/m <sup>2</sup>

##### THERMAL

Deflection Temperature, unannealed. 264 psi (1.8 MPa), Load	ISO 75	131	°C
--	--------	-----	----