

## MAXTEL 600T18

MAXTEL 600T18 is 18% talc filled TPO. This material is available in black. It can be color matched black and either UV or non-UV stable. It is typically used for automotive interior/exterior mold in color and painted applications. Please contact us for additional information.

### Typical ISO Properties

#### Properties

##### PHYSICAL

	Test Method		S. I. Units
Specific Gravity	ISO 1183	1.05	NA
Melt Flow Rate @ 230 °C/2.16kg	ISO 1133	22	g/10min
Reinforcement Content	ISO 3451	18	%

##### MECHANICAL

Tensile Strength @ Yield	ISO 527	18	MPa
Flexural Strength	ISO 178	27	MPa
Flexural Modulus	ISO 178	1,500	MPa
Izod Impact, notched	ISO 180	32	kJ/m <sup>2</sup>

##### THERMAL

Deflection Temperature, 66 psi (.45 MPa), Load	ISO 75	96	°C
---	--------	----	----