

## NAXELL PC210MR

NAXELL PC210MR is available in black color, internal and external lubricants and other modifications. Further information and details are available upon request.

### Typical ISO Properties

#### Properties

#### PHYSICAL

	Test Method		S. I. Units
Specific Gravity	ISO 1183	1.2	NA
Melt Flow Rate @ 250 °C/5.0kg	ISO 1133	20	g/10min

#### MECHANICAL

Tensile Strength @ Yield	ISO 527	60	MPa
Flexural Strength	ISO 178	96	MPa
Flexural Modulus	ISO 178	2,343	MPa
Izod Impact, notched	ISO 180	40	kJ/m <sup>2</sup>

#### THERMAL

Deflection Temperature, unannealed. 0.125" (3.2mm) 264 psi (1.8 MPa), Load	ISO 75	125	°C
---	--------	-----	----