

## MAXTEL 600T20

MAXTEL 600T20 is 20% talc filled TPO. This material is available in standard gray or black, color match gray or black, and with or without UV. It is typically used for automotive interior/exterior applications. Please contact us for additional information.

### Typical ISO Properties

#### Properties

#### PHYSICAL

	Test Method		S. I. Units
Specific Gravity	ISO 1183	1.05	NA
Melt Flow Rate @ 230 °C/2.16kg	ISO 1133	18	g/10min
Reinforcement Content	ISO 3451	20	%

#### MECHANICAL

Tensile Strength @ Yield	ISO 527	18	MPa
Flexural Strength	ISO 178	26	MPa
Flexural Modulus	ISO 178	1,500	MPa
IZOD Impact, notched	ISO 180	23	kJ/m <sup>2</sup>

#### THERMAL

Deflection Temperature, unannealed. 0.125" (3.2mm) 264 psi (1.8 MPa), Load	ISO 75	52	°C
---	--------	----	----